

# **Super Satin (Matt)**

# **Clear Polyurethane Coating**

# **Description**

A two-component waterborne polyurethane formulated to provide an ultra-durable clear coating with a matt finish.

### **Benefits**

- Long pot life.
- Environmentally and user friendly (solvent free).
- Excellent mar resistance.
- Matt / Satin finish.
- Easy cleaning good stain resistance.

#### Resistance

- Good resistance to spillages of most dilute solutions of acid and alkalis.
- Good resistance to aliphatic solvents, alcohols, grease and oil.
- Resistant to cleaning chemicals at recommended dilutions.
- Good stain resistance to foodstuff such as coffee, tomato sauce, mustard etc.

#### **Substrate Requirements**

- Old or new concrete must be clean and mechanically sound, free of dust, laitance and oil contamination.
- Grinding or shot blasting is recommended.
- All omegas, blow holes or cracks to be filled with Aquapaste and smoothed off prior to priming.
- Existing coatings must be washed, rinsed and abraded with a diamond grinder.

#### Concrete

# Floor Finishes:

When used as a matt sealer onto existing epoxy on PU floor finishes, ensure surface is abraded with 40 grit paper and solvent wiped immediately, prior to application.

# **Products Included in this System**

Super Satin PU Base + Activator.

Detailed application instructions are available upon request.

Flowcrete SA (Pty) Ltd is a subsidiary of Flowcrete Group plc

Durban
176 Voortrekker Street
Jacobs
Durban
Kwa Zulu Natal
Tel: +27 31 461 3411
Fax: +27 31 461 3475
Email: southafrica@flowcrete.com

47 Forge Road Spartan Gauteng Tel: +27 11 394 1980 Fax: +27 11 394 3003

**Johannesburg** 

Cape Town
1A Gabriel place
Cnr Gabriel & Main Road
Plumstead
Cape Town
Tel: +27 21 797 0214
Fax: +27 21 761 6664

#### **Technical Information**

The figures that follow are typical properties achieved in laboratory tests at 20  $^{\circ}$ C and at 50% Relative Humidity.

No of components: 2
Mixing Ratio (by volume): 9:1
Pot life: 2 hours
Touch dry: 3 hours
Overcoat time: 6 hours
Practical cure: 12 hours

Apply by:

Brush or mohair

roller

Coverage: 8-10m²/ℓ per coat
D.F.T per coat @ 8m²/ℓ: ±40 microns
Application temperature: 10-30°C
Number of coats: 2
Cleaner: Water
Shelf life: 12 months

# **Installation Service**

The installation should be carried out by a Flowcrete approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our web site www.flowcrete.com.

#### Important Note

Flowcrete's products are guaranteed against defective materials and the finished product.

## **Further Information**

To ensure you are specifying a fit for purpose flooring for your project please consult our Technical Advisors on the number below or visit our website to register your interest in specifying one of the most durable floors on the market.