

IVORY 340/5/LV

Low Viscosity Solvent Free Penetrating Epoxy System

PRODUCT DATA SHEET

Description

A low viscosity, solvent free, penetrating epoxy system.

Uses

For the saturation and penetration of timber and ply wood to seal and strengthen.

Preparation

Surfaces to be clean, sound and dust free and have a maximum moisture content of 4%.

Application

- Thoroughly mix together only enough product which can be applied in 20 minutes at 25°C.
- Apply by brush or roller, applying successive coats wet on wet until no further absorption of epoxy occurs.
- Should over 18 hours lapse between the coating of the Ivory 340/5/LV and the top coat or finish coat the surface of the previous coating must be abraded with a medium grit abrasive paper and solvent wiped using epoxy thinners.

Health & Safety

Some of the components of this product may be hazardous during mixing and application. Please consult the relevant Health & Safety Data Sheet available from Flowcrete on request and sent with each delivery.

Properties

No of components:	2
Mixing Ratio:	
Epoxy/Activator by volume	2:1
Pot life (250ml @ 25°C):	20 mins
Apply by:	Brush or roller
Theoretical Coverage:	Depends on the density of the timber
Overcoat time:	Wet on wet
Over coating time for top	
Coat or finish coat:	Min 6 hours
	Max 18 hours
Colour:	Clear
Cleaner:	Ivory W.S.B.C.
Shelf life:	12 months

Durban

176 Voortrekker Street
Jacobs
Durban
Kwa Zulu Natal
Tel: +27 31 461 3411
Fax: +27 31 461 3475
Email: southafrica@flowcrete.com
Flowcrete SA (Pty) Ltd is a subsidiary of Flowcrete Group plc

Johannesburg

47 Forge Road
Spartan
Gauteng
Tel: +27 11 394 1980
Fax: +27 11 394 3003

Cape Town

1A Gabriel place
Cnr Gabriel & Main Road
Plumstead
Cape Town
Tel: +27 21 797 0214
Fax: +27 21 761 6664