

Conrep SF65 Non Shrink Cementitious Grout

Description

Conrep S.F. 65 is a ready for use, non-shrink and cementitious grout. Conrep S.F. 65 is formulated using selected aggregates and plasticizers resulting in high flow ability with minimum water additions ensuring high compressive strengths.

Uses

All grouting applications requiring no shrinkage, good flow ability and high compressive strength of which typical applications are:

- Grouting and bedding of machine pump and column bases.
- Grouting holding down bolts and any applications requiring a fine grout.
- Grouting and repairing cavities and honeycombing in concrete.

Benefits

- Non Bleeding.
- Chloride Free.
- Non-Shrink.
- Pourable and pumpable.
- · Volumetrically stable after 24 hours.

Substrate Requirements

Contact surfaces to be clean and free from oil, dust or shutter release agents and concrete surfaces to be chipped or scarified to remove laitance. Concrete surfaces to be thoroughly presoaked but all surface water to be removed before application of grout. A minimum gap of 20mm between concrete bed and base plate or between bolt and cavity side is necessary, with provision for release of entrapped air being made.

Mixing of Grout

Mixing of grout to be by pan or slow speed drum mixer. 75% of gauged water added to mixing vessel followed by the dry grout and mixed until free of lumps. Add remaining water and mix to required consistency.

Flowcrete SA (Pty) Ltd 47 Forge Road Spartan Gauteng

Tel: +27 11 394 1980 Fax: +27 11 394 3003

Technical Information

The figures that follow are typical properties achieved in laboratory tests at 20 $^{\circ}$ C and at 50% Relative Humidity.

Colour: Natural

Yield: 25kg yields 13l

Water requirements: 3½ - 4½25kg grout depending on flow

requirements

Expansion: $\pm 1\%$ in 24 hours,

therefore un-changed

Time of final set: 5 hours

Typical compressive

strength: 1 day 28mPa 3 days 42mPa

7 days 55mPa 28 days 65mPa 2kg/ ℓ

Shelf life: 6 months in dry cool

storage

Placing of Grout

Density:

Immediately after mixing, the grout is to be poured into the cavity at one point only to avoid entrapping air. Any grout too stiff to place must be discarded and not re-mixed. Complicated grouting situations may require "strapping" to assist flow ability. This is to be undertaken with a flexible length of thin metal or plastic.

Grout Curing

Grout surface must be kept wet and protected from sun and wind to prevent rapid drying. Cover surface with plastic membrane, damp Hessian or spray with a curing compound.

Further Information

To ensure you are specifying a fit for purpose flooring for your project please consult our Technical Advisors on the number below or visit our website to register your interest in specifying one of the most durable floors on the market.

Flowcrete SA (Pty) Ltd 176 Voortekker Street Jacobs Durban Kwa Zulu Natal

Tel: +27 31 461 3411 Fax: +27 31 461 3475 Flowcrete SA (Pty) Ltd 1A Gabriel place Cnr Gabriel & Main Road Plumstead Cape Town

Tel: +27 21 797 0214 Fax: +27 21 761 6664