



**Robex S.A.**  
(PTY) LTD. REG:2002/012975/07

Unit 2  
No. 6 Middle Muir Road  
Anderbolt 1459

P.O. Box 2082  
Boksburg 1460

Tel: +27 (0)11 892 - 2604 / 2565  
Fax: +27 (0)11 917 - 1474

## **ROBEX P2000**

### **FEATURES AND BENEFITS OF ROBEX FLOORGUARD P2000**

1. Robex Floorguard P2000 is a heavy to medium duty, flow applied, smooth flooring system based upon polyurethane technology.
2. Provides excellent resistances to abrasion, chemical attack and any other physical aggression.
3. Robex Floorguard P2000 is volatile free, both during and after application, so work can be carried on in adjacent areas without fear of contamination.
4. Robex Floorguard P2000 is formulated to achieve maximum strength within minimum time, and with minimal disruption to your production cycle.
5. Unlike concrete surfaces that dust when worn, Robex Floorguard P2000 creates an impervious, hardwearing finish that lasts and lasts.
6. The appearance is seamless, smooth, high gloss finish with uniform colour.
7. Robex is designed for application between 2 & 6mm.
8. Is ideally suited to areas subject to heavy duty use: Chemical processing, Engineering process areas, Production areas etc.

### **PROCEDURES AND PREPARATIONS:**

1. The complete area will be mechanically abraded to remove the existing coating and any contaminants which could affect adhesion.
2. The entire floor area will be primed with Robex Floorguard Primer at 250 microns with 0.3 – 0.6 aggregate scattered into the wet primer and left to cure for 12 hours.
3. Once cured, Robex Floorguard P2000 will be applied at 2mm over the entire floor areas and left to cure for 24 – 48 hours.